

| <b>BASIC WEIGHT G/M2</b> | <b>THICKNESS MM</b> | <b>STRENGTH KN/M</b>       | <b>COMPOSITION</b> | <b>MOISTURE REGAIN %</b> | <b>FLAMMABILITY</b>         |
|--------------------------|---------------------|----------------------------|--------------------|--------------------------|-----------------------------|
| <b>100</b>               | <b>8</b>            | <b>MD:0.60<br/>CD:0.45</b> | <b>PP+PET</b>      | <b>0.38</b>              | <b>Conform to GB8410-94</b> |
| <b>200</b>               | <b>16</b>           | <b>MD:0.80<br/>CD:0.60</b> | <b>PP+PET</b>      | <b>0.38</b>              | <b>Conform to GB8410-94</b> |
| <b>400</b>               | <b>32</b>           | <b>MD:1.0<br/>CD:0.80</b>  | <b>PP+PET</b>      | <b>0.38</b>              | <b>Conform to GB8410-94</b> |
| <b>600</b>               | <b>50</b>           | <b>MD:2.2<br/>CD:0.90</b>  | <b>PP+PET</b>      | <b>0.38</b>              | <b>Conform to GB8410-94</b> |