


CUR 06

Curekind MBS(NOBS)

DESCRIPTION	Items		Specification	
	 N-Oxydiethyl-2-benzthiazolsulfenamid $C_{11}H_{12}N_2S_2O$ M.W. 253.35 CAS No.: 102-77-2 EINECS No.203-052-4	Appearance		Light yellow Granule
		Initial Melting Point, °C min.		78.0
		Heat Loss, % max.		0.50
		Ash, % (800 °C 2hr) max.		0.30
		Density, g/cm ³		1.35
		Residue on 830µm, % max		-

Characteristics Curekind®MBS(NOBS) is light-yellow granules, Easy to soluble in dichloromethane, acetone, soluble in benzene, carbon tetrachloride, ethyl acetate and alcohol, a little soluble in gasoline, insoluble in water. It will be gradually decomposition when being heated.

Application Curekind®MBS(NOBS) is a fast curing accelerator with a delayed action, especially suitable for the basic furnace carbon black natural rubber and synthetic rubber, can improve the rubber's physical and anti-aging properties, can be used on tire etc rubber parts.

Safety and Toxic Refer to the MSDS

Storage Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag. N.W.25kg/bag; N.W.500kg/pallet.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.