CUR 30



Curekind ZMBI (MBZ)

DESCRIPTIO	$\left[\bigcirc_{-N}^{-N} \geqslant c - s - z_{n} \\ \downarrow_{H}^{-N} \right]_{2}^{2}$	Items	Specification	
			Powder	Dust free Powder
		Appearance	White powder	
		Initial Melting Point,℃ min.	240.0	240.0
	Zinesaltof2-mercaptobenzi midazole C ₁₄ H ₁₀ N ₄ S ₂ Zn M.W. 363.77 CAS No.: 3030-80-6 EINECS No: 221-203-2	Heat Loss,% max.	1.50	0.50
		Ash,% (800°C 2hr)	26.0-28.5	26.5-28.5
		Density, g/cm ³	1.39	1.39
O N		Residue on150µm,% max.	0.10	0.10
		Residue on 63µm,% max.	0.50	0.50
		Additive, %	-	1.0-2.0

Characteristics Curekind[®]ZMBI is white powder, no smell but taste bitter. Soluble in acetone, alcohol, insoluble in benzene gasoline and water.

- Application Curekind[®]ZMBI, as a non-staining secondary antioxidant application for NR, CR, SBR, NBR and Latex etc. Curekind[®]ZMBI has the same effect with MB, which can decompose peroxide.
- Safety and Toxic Refer to the MSDS
- **Storage** Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag. N.W.25kg/bag;N.W.500kg/pallet.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.

Curekind[®]ZMBI(MBZ)

TECHNICAL DATA SHEET (TDS) version 1.3

Ningbo Actmix Rubber Chemicals Co., Ltd.

TEL:+86-574-87576736 FAX:+86-574-88002102 Email:dychem@actmix.cn <u>Http://www.actmix.cn/</u>