

Type	Basic W. g/m2	Thickness mm	Stiffness mg	0.38μm@85L/min-dm2		Application	Remarks
				Resistance Pa	Efficiency %		
45	115	0.85	1000	15	48%	F5	PP and PET ultrasonic melting
65	120	0.88	1200	18	68%	F6	
85	130	0.91	1500	21	80%	F7	
95	140	0.93	1800	35	85%	F8	
98	145	0.95	1800	40	90%	F9~Y10	
C85	110	0.78	1200	45	92%	Y10~Y11	PP and PET ultrasonic melting or hot-melt fiber adhesive
C195	115	0.80	1600	50	99%		
C295	120	0.82	1650	50	99.8%	Y12	
C395	130	0.85	1700	65	99.98%	Y13	