

Product Description

1>.Air filter paper

Item	Value
BASIS WEIGHT(g/m ²)	100~145
THICKNESS(mm)	≥0.40
AIR PERMEABILITY(p=200paL/m ² .s)	≥400
CORRUGATED DEPTH(mm)	0.25
BURST STRENGTH(Kpa)	≥200
MAXIMUM PORE SIZE(um)	100
RESIN CONTENT(%)	27

2>.Oil filter paper

Item	Value
BASIS WEIGHT(g/m ²)	100~145
THICKNESS(mm)	≥0.40
AIR PERMEABILITY(p=200paL/m ² .s)	≥400
CORRUGATED DEPTH(mm)	0.25
BURST STRENGTH(Kpa)	≥200
MAXIMUM PORE SIZE(um)	110
RESIN CONTENT(%)	27

3>.Air & oil filter paper

Item	Value
BASIS WEIGHT(g/m ²)	100~145
THICKNESS(mm)	≥0.40
AIR PERMEABILITY(p=200paL/m ² .s)	≥400
CORRUGATED DEPTH(mm)	0.25
BURST STRENGTH(Kpa)	≥200
MAXIMUM PORE SIZE(um)	110
RESIN CONTENT(%)	27

4>.Fuel filter paper

Item	Value
BASIS WEIGHT(g/m ²)	130~150
THICKNESS(mm)	≥0.40
AIR PERMEABLITY(p=200paL/m ² .s)	≤150
CORRUGATED DEPTH(mm)	0.25
BURST STRENGTH(Kpa)	≥300
MAXIMUM PORE SIZE(um)	110
RESIN CONTENT (%)	27